

Pandia®

Single-mode fiber compliant with ITU-T G.652.D and ITU-T G.657.A1

Physical Characteristics:

Clad Diameter:	$125.0 \pm 0.7 \mu\text{m}$
Clad Non-Circularity:	$\leq 0.7 \%$
Core-Clad Conc. Error:	$\leq 0.5 \mu\text{m}$
Coating Diameter (uncolored):	$237 - 247 \mu\text{m}$
Coating-Clad Conc. Error:	$\leq 12 \mu\text{m}$
Tensile Proof Test:	100 kpsi (0.69 GPa)
Coating Strip Force Range:	$1.0 \text{ N} \leq \text{CSF} \leq 8.9 \text{ N}$
Standard Reel Lengths:	50.4 km

Environmental Characteristics (at 1310, 1550 and 1625 nm):

- Temperature Cycling (-60 °C to +85 °C) $\leq 0.05 \text{ dB/km}$
- High Temperature Aging (85 ± 2 °C) $\leq 0.05 \text{ dB/km}$
- Temperature & Humidity Cycling (at -10 °C to +85 °C, and 95 % RH) $\leq 0.05 \text{ dB/km}$
- Water Immersion (23 ± 2 °C) $\leq 0.05 \text{ dB/km}$
- Dynamic Fatigue Stress Corrosion Parameter $n_d \geq 20$

Attenuation Characteristics:

	Maximum	Typical
1310 nm	$\leq 0.34 \text{ dB/km}$	$\leq 0.33 \text{ dB/km}$
1385 nm	$\leq 0.31 \text{ dB/km}$	$\leq 0.27 \text{ dB/km}$
1490 nm	$\leq 0.24 \text{ dB/km}$	$\leq 0.21 \text{ dB/km}$
1550 nm	$\leq 0.20 \text{ dB/km}$	$\leq 0.19 \text{ dB/km}$
1625 nm	$\leq 0.23 \text{ dB/km}$	$\leq 0.20 \text{ dB/km}$

Point Discontinuities 1310 nm, 1550 nm $\leq 0.05 \text{ dB}$

Attenuation vs. Wavelength:

Range	Reference	Max Difference α
1285 – 1330 nm	1310 nm	$\leq 0.03 \text{ dB/km}$
1525 – 1575 nm	1550 nm	$\leq 0.02 \text{ dB/km}$

The attenuation in a given wavelength range does not exceed the attenuation of the reference wavelength by more than the value α .

Macrobend Performance:

Bending-induced attenuation does not exceed the specified values under the following deployment conditions:

Deployment Condition	Wavelength	Induced Attenuation
1 turn on 10 mm radius mandrel	1550 nm	$\leq 0.75 \text{ dB}$
	1625 nm	$\leq 1.5 \text{ dB}$
10 turns on 15 mm radius mandrel	1550 nm	$\leq 0.25 \text{ dB}$
	1625 nm	$\leq 1.0 \text{ dB}$
100 turns on 25 mm radius mandrel	1550 nm	$\leq 0.03 \text{ dB}$
	1625 nm	$\leq 0.03 \text{ dB}$

Other Characteristics:

Zero Dispersion Wavelength λ_0 :	1302 – 1322 nm
Zero Dispersion Slope S_0 :	$\leq 0.090 \text{ ps/nm}^2 \cdot \text{km}$
Fiber PMD Link Design Value:	$\leq 0.04 \text{ ps}/\text{km}$
Maximum Individual Fiber PMD:	$\leq 0.1 \text{ ps}/\text{km}$
Mode Field Diameter (1310 nm):	$9.2 \pm 0.4 \mu\text{m}$
Mode Field Diameter (1550 nm):	$10.4 \pm 0.5 \mu\text{m}$
Cable Cut-Off Wavelength λ_{cc} :	$\leq 1260 \text{ nm}$



Denmark

Heraeus Comvance Denmark ApS

Priorparken 611

2605 Brøndby

Phone +49 6181 35 8307

comvance.dk@heraeus.com

www.heraeus-comvance.com

Pandia® 190

Single-mode fiber compliant with ITU-T G.652.D and ITU-T G.657.A1

Physical Characteristics:

Clad Diameter:	$125.0 \pm 0.7 \mu\text{m}$
Clad Non-Circularity:	$\leq 0.7 \%$
Core-Clad Conc. Error:	$\leq 0.5 \mu\text{m}$
Coating Diameter (uncolored):	$180 - 200 \mu\text{m}$
Coating-Clad Conc. Error:	$\leq 10 \mu\text{m}$
Tensile Proof Test:	100 kpsi (0.69 GPa)
Coating Strip Force Range:	$1.0 \text{ N} \leq \text{CSF} \leq 8.9 \text{ N}$
Standard Reel Lengths:	50.4 km

Environmental Characteristics (at 1310, 1550 and 1625 nm):

- Temperature Cycling (-60 °C to +85 °C) $\leq 0.05 \text{ dB/km}$
- High Temperature Aging (85 ± 2 °C) $\leq 0.05 \text{ dB/km}$
- Temperature & Humidity Cycling (at -10 °C to +85 °C, and 95 % RH) $\leq 0.05 \text{ dB/km}$
- Water Immersion (23 ± 2 °C) $\leq 0.05 \text{ dB/km}$
- Dynamic Fatigue Stress Corrosion Parameter $n_d \geq 20$

Attenuation Characteristics:

	Maximum	Typical
1310 nm	$\leq 0.34 \text{ dB/km}$	$\leq 0.33 \text{ dB/km}$
1385 nm	$\leq 0.31 \text{ dB/km}$	$\leq 0.27 \text{ dB/km}$
1490 nm	$\leq 0.24 \text{ dB/km}$	$\leq 0.21 \text{ dB/km}$
1550 nm	$\leq 0.20 \text{ dB/km}$	$\leq 0.19 \text{ dB/km}$
1625 nm	$\leq 0.23 \text{ dB/km}$	$\leq 0.20 \text{ dB/km}$

Point Discontinuities 1310 nm, 1550 nm $\leq 0.05 \text{ dB}$

Attenuation vs. Wavelength:

Range	Reference	Max Difference α
1285 – 1330 nm	1310 nm	$\leq 0.03 \text{ dB/km}$
1525 – 1575 nm	1550 nm	$\leq 0.02 \text{ dB/km}$

The attenuation in a given wavelength range does not exceed the attenuation of the reference wavelength by more than the value α .

Macrobend Performance:

Bending-induced attenuation does not exceed the specified values under the following deployment conditions:

Deployment Condition	Wavelength	Induced Attenuation
1 turn on 10 mm radius mandrel	1550 nm	$\leq 0.75 \text{ dB}$
	1625 nm	$\leq 1.5 \text{ dB}$
10 turns on 15 mm radius mandrel	1550 nm	$\leq 0.25 \text{ dB}$
	1625 nm	$\leq 1.0 \text{ dB}$
100 turns on 25 mm radius mandrel	1550 nm	$\leq 0.03 \text{ dB}$
	1625 nm	$\leq 0.03 \text{ dB}$

Other Characteristics:

Zero Dispersion Wavelength λ_0 :	1302 – 1322 nm
Zero Dispersion Slope S_0 :	$\leq 0.090 \text{ ps/nm}^2 \cdot \text{km}$
Fiber PMD Link Design Value:	$\leq 0.04 \text{ ps}/\text{km}$
Maximum Individual Fiber PMD:	$\leq 0.1 \text{ ps}/\text{km}$
Mode Field Diameter (1310 nm):	$9.2 \pm 0.4 \mu\text{m}$
Mode Field Diameter (1550 nm):	$10.4 \pm 0.5 \mu\text{m}$
Cable Cut-Off Wavelength λ_{cc} :	$\leq 1260 \text{ nm}$



Denmark

Heraeus Comvance Denmark ApS

Priorparken 611

2605 Brøndby

Phone +49 6181 35 8307

comvance.dk@heraeus.com

www.heraeus-comvance.com